

- IATF16949
- ISO9001
- ISO13485
- ISO14001
- ISO50001

INDUSTRIES AND APPLICATIONS



THERMOFLEX HRI MARDER

Typical uses


- Automotive industry
- Crash protection
- E-mobility / hybrid
- Cable manufacture
- Line protection
- Commercial vehicles

Key properties

- Institute-tested against marten bites
- Long-term heat resistance of -40°C to +210°C
- Short-term heat resistance up to +235°C
- Abrasion classification A, LV 312-3
- Thick walled, very good insulated, possible in double walled version
- Excellent crash protection
- Good abrasion resistance
- High buckling resistance, cut resistance and impact resistance
- Good resistance to water, water-glycol mixture, salt spray, as well as to fuels and lubricants during temporary exposure
- Nominal diameter 5.0 mm to 30.0 mm



Application temperature



Product description

THERMOFLEX HRI MARDER consists of high thermal load resistant and special braided textile glass fibre with a unique silicone resins impregnation. The combination of these materials allows the use of the sleeve in automotive line protection against marten bites as well as crash protection. Even in extreme situations (short-term) the sleeve resists a thermal load up to 235°C. The colour may change (orange) at temperatures above 210°C. The THERMOFLEX HRI MARDER is characterized by good resistance against a short-term contact with fuels and lubricants. Water and salt spray does not affect the function of the sleeve. THERMOFLEX HRI MARDER is suitable for longer cable sets because of its good buckling resistance.

- IATF16949
- ISO9001
- ISO13485
- ISO14001
- ISO50001

INDUSTRIES AND APPLICATIONS



THERMOFLEX HRI MARDER

Application properties

Property	Standard	Test requirements	Result
Flame resistance	LV 312-3 FMVSS 302	Flame height 38 mm Flame exposure 15s	Requirements achieved

Mechanical / physical properties

Property	Standard	Test requirements	Result
Abrasion resistance	LV 312-3 ISO 6722-1	Tested at room temperature	Classification A

Compatibilities

Medium	Standard	Test requirements	Result
Ad Blue	LV 312-3	Storage 240h, 480h, 180 °C Winding test	Requirements achieved
Biodiesel	LV 312-3	Storage 240h, 480h, 180 °C Winding test	Requirements achieved
Break fluid	LV 312-3	Storage 240h, 480h, 180 °C Winding test	Requirements achieved
Diesel	LV 312-3	Storage 240h, 480h, 180 °C Winding test	Requirements achieved
Cold cleaning agent	LV 312-3	Storage 240h, 480h, 180 °C Winding test	Requirements achieved
Fuel FAM-B	LV 312-3	Storage 240h, 480h, 180 °C Winding test	Requirements achieved
Penetrating oil	LV 312-3	Storage 240h, 480h, 180 °C Winding test	Requirements achieved
Radiator antifreeze	LV 312-3	Storage 240h, 480h, 180 °C Winding test	Requirements achieved
Grease	LV 312-3	Storage 240h, 480h, 180 °C Winding test	Requirements achieved
Water-Glycol-mixture	LV 312-3	Storage 240h, 480h, 180 °C Winding test	Requirements achieved

- IATF16949
- ISO9001
- ISO13485
- ISO14001
- ISO50001

INDUSTRIES AND APPLICATIONS



THERMOFLEX HRI MARDER

Ecology, Environment & Safety

Ingredients compliant with VDA - requirements

IMDS listed

RoHS, GADSL compliant

Non-asbestos, textile glass fibres non-carcinogenic, non-hazardous to the environment, non-hazardous to water.

The textile glass sleeve requires compliance with the industrial hygiene. Workplace ventilation has to be turned away from the worker, sensitive individuals may get slight skin irritation.

When using and disposing of THERMOFLEX HRI MARDER protective sleeve there are no environmentally relevant by-products expected.

BIW-Standard dimensions

THERMOFLEX HRI MARDER (Code: GHZ)

On demand individual dimensions available at any time

ID [mm]	Tol. ID [mm]	Wd [mm]	Tol. Wd [mm]	Ring [m]
5.0	±0.30	0.7	±0.30	100
6.0	±0.30	1.0	±0.30	100
7.0	±0.30	1.0	±0.30	100
8.0	±0.30	1.0	±0.30	100
9.0	±0.30	1.0	±0.30	50
10.0	±0.50	1.0	±0.30	50
11.0	±0.50	1.0	±0.30	50
12.0	±0.50	1.0	±0.30	50
13.0	±0.50	1.0	±0.30	50
14.0	±0.50	1.0	±0.30	50
15.0	±0.50	1.0	±0.30	50
16.0	±0.50	1.0	±0.30	50
17.0	±0.50	1.0	±0.30	50
18.0	±0.50	1.0	±0.30	50
19.0	±0.50	1.0	±0.30	50
20.0	±0.70	1.0	±0.30	50
21.0	±0.70	1.0	±0.30	50
22.0	±0.70	1.0	±0.30	50
23.0	±0.70	1.0	±0.30	25

(Continued on the next page)

BIW Isolierstoffe GmbH

Pregelstraße 2-5
D-58256 Ennepetal
Tel.: +49 (2333) 8308-0
Fax.: +49 (2333) 8308-10
info@biw.de
www.biw.de

Certified management system by:

- IATF16949
- ISO9001
- ISO13485
- ISO14001
- ISO50001



TECHNICAL DATASHEET

INDUSTRIES AND APPLICATIONS



THERMOFLEX HRI MARDER

BIW-Standard dimensions

THERMOFLEX HRI MARDER (Code: GHZ)

On demand individual dimensions available at any time

ID [mm]	Tol. ID [mm]	Wd [mm]	Tol. Wd [mm]	Ring [m]
24.0	±0.70	1.0	±0.30	25
25.0	±0.70	1.0	±0.30	25
26.0	±0.70	1.0	±0.30	25
27.0	±0.70	1.0	±0.30	25
28.0	±0.70	1.0	±0.30	25
29.0	±0.70	1.0	±0.30	25
30.0	±0.80	1.3	±0.30	25